

EVA

特性 Characteristics

2825 为乙烯-醋酸乙烯酯共聚物, 由 Basell 管式法工艺生产, 透明性好, 晶点少, 易加工。

V2825 is an ethylene-vinyl acetate copolymer (EVA) produced by Tubular process licensed by Basell. It offers good transparency, less gels, good processibility.

应用 Applications

光伏膜 solar photovoltaic cell encapsulant film

性能 Properties

项 目 Properties	单位 Unit	典型值 Typical Value	测试方法 Test Method
VA 含量 VA content	wt. %	28	GB/T 30925
熔融指数 Melt Index	g/10min	25	Sierbang method
拉伸断裂强度 Tensile Strength at Break	MPa	9.2	GB/T 1040
拉伸断裂伸长率 Elongation at Break	%	880	GB/T 1040
维卡软化温度 Vicat Softening Point	℃	37	GB/T 1633
熔点 Melt Point	℃	69	GB/T 19466