



特性 Characteristics

2806 为乙烯-醋酸乙烯酯共聚物, 由 Basell 管式法工艺生产, 弹性好, 晶点少, 易加工。
V6020M is an ethylene-vinyl acetate copolymer (EVA), produced by Tubular process licensed by Basell. It offers good elasticity, less gels, good processibility.

应用 Applications

1. 电线电缆 wire and cable
2. 发泡 foaming

性能 Properties

项 目 Properties	单位 Unit	典型值 Typical Value	测试方法 Test Method
VA 含量 VA contents	wt. %	28	GB/T 30925
熔融指数 Melt Index	g/10min	6	Sierbang method
拉伸断裂强度 Tensile Strength at Break	MPa	12. 1	GB/T 1040
拉伸断裂伸长率 Elongation at Break	%	840	GB/T 1040
维卡软化温度 Vicat Softening Point	℃	41	GB/T 1633
熔点 Melt Point	℃	73	GB/T 19466